

## **AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions and listings of claims in the application:

1. (Currently amended) A nonwoven fabric comprising a thermoplastic synthetic fiber nonwoven fabric having a fabric weight of 7 to 50 g/m<sup>2</sup>, an average fiber diameter of 7 to 40 μm, a partial heat contact bonding ratio of 5 to 30% and a content of a delustering agent of 0.5% by weight or less, wherein the nonwoven fabric is a laminate of a thermoplastic synthetic fiber spun-bonded nonwoven fabric having an average fiber diameter of 7 to 15 μm and a thermoplastic synthetic fiber spun-bonded nonwoven fabric having an average fiber diameter of 15 to 40 μm, wherein the nonwoven fabric has a variation ratio of a fabric weight, 10 cm x 10 cm, of 10% or less and wherein the nonwoven fabric has a maximum opening diameter of 200 to 2,000 μm, and shows a transparency of 50% or more, a powder leakage ratio of 10% by weight or less and a hydrophilicity of less than 10 sec.

2. (Currently amended) The nonwoven fabric according to claim 1, wherein the nonwoven fabric is a thermoplastic synthetic fiber nonwoven fabric having a fabric weight of 12 to 30 g/m<sup>2</sup>, an average fiber diameter of 12 to 30 μm, a partial heat contact bonding ratio of 5 to 30% and a content of a delustering agent of 0.2% by weight or less, wherein the nonwoven fabric is a laminate of a thermoplastic synthetic fiber spun-bonded nonwoven fabric having an average fiber diameter of 12 to 15 μm and a thermoplastic synthetic fiber spun-bonded nonwoven fabric having an average fiber diameter of 15 to 30 μm, and wherein the nonwoven fabric has a maximum

opening diameter of 400 to 1,650  $\mu\text{m}$ , and shows a transparency of 60% or more, a powder leakage ratio of 5% by weight or less and a hydrophilicity of less than 10 sec.

3. (Cancelled).

4. (Currently amended) The nonwoven fabric according to ~~any one of~~ ~~claims claim 1 [[to 3]] or 2~~, wherein the thermoplastic synthetic fiber spun-bonded nonwoven fabric is a spun-bonded nonwoven fabric composed of a polyolefin filament fiber.

5. (Currently amended) The nonwoven fabric according to ~~any one of~~ ~~claims claim 1 [[to 3]] or 2~~, wherein the thermoplastic synthetic fiber spun-bonded nonwoven fabric is a spun-bonded nonwoven fabric composed of a polyester filament fiber.

6. (Currently amended) The nonwoven fabric according to claim 5, wherein the thermoplastic synthetic fiber spun-bonded nonwoven fabric is a spun-bonded nonwoven fabric composed of an aliphatic polyester filament fiber.

7. (Previously presented) The nonwoven fabric according to claim 6, wherein the aliphatic polyester filament fiber is a filament fiber of a polyester selected from a poly(D-lactic acid), a poly(L-lactic acid), a copolymer of D-lactic acid and L-lactic acid, a copolymer of D-lactic acid and a hydroxycarboxylic acid, a copolymer of L-lactic acid and a hydroxycarboxylic acid, a copolymer of D-lactic acid, L-lactic acid and a hydroxycarboxylic acid, or a blend of these polymers.

8. (Currently amended) The nonwoven fabric according to ~~any one of~~ ~~claims claim 1 [[to 3]] or 2~~, wherein a synthetic resin or a fibrous material of 2 to 15  $\text{g/m}^2$

having a melting point lower than that of the thermoplastic synthetic fiber by 30 to 200°C is laminated to the thermoplastic synthetic fiber nonwoven fabric.

9. (Currently amended) A tea bag prepared by filling a tea material, to be extracted, into a bag composed of the nonwoven fabric according to claim 1 or 2, and sealing the tea material.

10. (Original) The tea bag according to claim 9, wherein the bag is tetrahedral-shaped.

11. (Previously presented) The tea bag according to claim 9, wherein the tea material to be extracted is black tea, green tea or oolong tea.